Overview:

Chinese name: FASCAT4233 catalyst,

Alias: FASCAT4233 catalyst, butyltin mercaptide

English name: 4233, Butylmercaptooxo stannane; Butyltin mercaptide



FASCAT4233 催化剂 FASCAT4233 catalyst



Physical and chemical properties:

Specific gravity (20℃) 1.13

Refractive index (20℃) 1.580

Sulfur (%) 17.5~18.5

Viscosity (20°C) 15

Butyl tin mercaptide, the appearance is colorless and transparent liquid, the molecular weight is 635.

- Clear to light colored liquid
- Highly selective for polyurethane systems.
- Hydrolytic stability for waterborne coatings and adhesives
- Formulations needing long pot life at room temperature, quick cure at elevated temperatures

use:

Add butyltin laurate maleate for use.

Storage and transportation:

It should be sealed and stored in a dry, cool and ventilated warehouse.

Package:

Packing: 25Kg cardboard drum.

Contact Us

SHANGHAI OHANS CO., LTD.

Factory Address: Jining High-tech Development Zone, Shandong, China

Call Center: 021-5161-9971

Web Site: www.tinchem.org

Headquarters: Room a2110, building 55, No. 709, Lingshi Road, Zhabei District,

Shanghai

Email Us: honda@ohans.com candy@ohans.com